



Cottura GRES rosso SAFF impasti ceramici

Temp.	MCR	AA
850	40,2	14,9
870	59,7	14,7
890	75,5	14,6
910	83,5	14,5
930	95,4	14,4
970	104,5	14,1
1000	113,5	13,8
1020	125,1	13,3
1060	197,1	12,5
1100	239	6,9
1115	254,4	2,6
1130		0,3

